

MATERIAL DATASHEET

(Revision 20-09-2023)

GENERAL PROPERTIES				
Compound name:	NDS-225			
Compound description:	PTFE + 25% carbon			
Color:	Dark grey			
Operating temperature range:	-190°C to +315°C			
Approvals/certifications:	n/a			

PHYSICAL PROPERTIES				
Property	Specified	Test result	Unit	Standard
Hardness	-	63	Shore D	-
Specific gravity	2,20+/-0,02	2.10	g/cm3	ASTM D 792
Tensile strength CD	≥14	-	N/mm2 (MPa)	ASTM D 638
Elongation at break CD	≥180	-	%	ASTM D 638
Deformation under load (140 Kg/cm² per 24 hours at 23°C)	5.0-6.0	-	%	ASTM D 621
Permanent deformation (24 hours at 23°C)	1.8-2.2	-	%	ASTM D 621
Coefficient of linear thermal expansion (T=25-100°C)	7.0-12.0	-	10-5/°C	ASTM D 696
Volume resistivity	104	-	Ω* cm	ASTM D 257
Coefficient of dynamic friction	0.11	-	-	ASTM D 1894 – 78
Wear coefficient (PV=100 (kg*m)/(cm³/min))	30-40	-	(cm3*min)/ (kg*m*h)*10 ⁻⁸	

In normal conditions: +23°C/50% relative humidity CD: Cross Direction

Disclaimer

Disclaimer
This information is to the best of our knowledge accurate to the date indicated. However, NewDealSeals make no warranty, expressed or implied that parts manufactured from this material will perform satisfactorily in the customer's application. It is the customer's responsibility to evaluate parts prior to use, especially in applications where their failure may result in injury and/or damage. It should also be noted that all elastomeric parts have a finite life, therefore a regular program of inspection and replacement is strongly recommended. TGA, infrared and other types of analysis must be agreed, fixed and approved by both parties with specifications and tolerances; on the contrary results can neither confirmed nor guaranteed. Nothing herein shall be construed as a recommendation to infringe any existing patent or violate any applicable law. The distribution of this document is not monitored. This data sheet is not subject to an automatic undate. monitored. This data sheet is not subject to an automatic update.

